

Temafloor PU-UV

DESCRIPTION

A high-solids, flexible and weather resistant two-component polyurethane coating.

PRODUCT FEATURES AND RECOMMENDED USES

- Excellent resistance to UV
- Silent, does not shrink or crack
- Withstands mechanical and chemical stress
- Self-levelling, to be applied with serrated or steel trowel
- Intended to be used as a UV-resistant topcoat on Temafloor PU floors in parking decks and other areas exposed to direct sunlight

TECHNICAL DATA

Volume solids

approx. 90%

Specific gravity

1.4 kg / litre (mixture)

Mixing ratio

Base	2 parts by volume	Temafloor PU-UV
Hardener	1 part by volume	008 4001

Pot life (+23°C)

40 minutes on substrate, abt. 20 minutes in the mixing container.

Practical coverage

Practical coverage depends on the porosity and evenness of the substrate and on the application method.

Film thickness 0.3mm coverage approx. 2.7 m²/litre

Film thickness 1.0mm coverage approx. 0.9 m²/litre

Drying time (+23°C)

Dust dry after 6 hours

Light trucking after 24 hours

Fully cured after 7 days

At lower temperatures the curing process will last longer.

Cleaning of equipment

Thinner 1061.

Finish

Gloss.

Colors

TVT 0229. For request RAL 3001, RAL 3020, RAL 7032, RAL 7040 and RAL 7045.
The shade and gloss of the coating may change during time

Thinning instructions

Do not thin Temafloor PU-UV polyurethane coating.

VOC

VOC 2004/42/EC (cat A/j)500 g/l (2010)

Temafloor PU-UV: max. VOC < 500 g/l

Can sizes

10,0 L, 20,0 L

Temafloor PU-UV

APPLICATION INSTRUCTIONS

Surface preparation

New concrete: Remove laitance by power grinding, vacuum grit blasting or hydrochloric acid etching. Choose the method best suited for the premises. After grinding remove dust carefully with a vacuum cleaner. Hydrochloric acid etching is carried out with diluted hydrochloric acid (1 part concentrated hydrochloric acid, 4 parts water). Rinse with plenty of water. Dry the floor.

Old concrete: Remove all grease, oil, chemicals and other impurities by Maalipesu detergent. Remove old peeling paint layer by grinding, milling or vacuum grit blasting. Choose the method best suited for the premises. Clean out pot-holes removing all loose friable material. Open cracks with e.g. an abrasive tool. Remove loose material and dust.

Earlier painted surfaces: Grind the surface. Remove dust and loose particles from the floor. Remove all grease, oil and other impurities by detergent washing.

Application conditions

The relative humidity of the concrete should not exceed 97%. The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 70%.

Mixing components

First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 2 minutes to get homogenous mixture) by using a low speed industrial hand drill with a paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.

Priming

Prime using Temafloor 400 epoxy varnish thinned 30–50% with Thinner 1029 or Fontefloor EP Primer epoxy varnish thinned about 20-50% with water. Pour the primer onto the floor and apply as much as is needed to impregnate the concrete surface. If necessary, repeat priming to get a non-porous surface. A porous priming coat will result in holes and air bubbles in the finished coating. Subsequent treatment can be carried out after 2 hours using "wet-on-wet" technique.

Asphalt floors should be primed by applying unthinned Temafloor PU with a suitable steel or rubber trowel.

Scatter sand of grain size Ø 0,1–0,6 mm on the fresh primer coat to ensure the screed adhesion. Remove loose sand with vacuum cleaner before coating with Temafloor PU-UV.

Patching

Patch pot-holes and cracks with unthinned Temafloor 400 epoxy varnish and dry, clean sand. Mixing ratio e.g. 1 part by volume of epoxy mixture and 1–2 parts by volume of sand of grain size Ø 0.1–0.6 mm. Sand the patched areas before overcoating, if necessary.

Note! Concrete surface should always be primed before patching.

Topcoating

Overcoating may be carried out not earlier than 24 hrs after coating with Temafloor PU. If the primed surface is not overcoated within 24 hrs, it should be abraded. Pour the mixture onto the floor and apply it with a trowel and level with a roller.

Control that the thickness of layer is correct by observing coating consumption and by measuring the film thickness. Recommended layer thickness is 0.3–1.0 mm. Use spiked roller to finish the surface approx. 10–20 min after application. Spiked roller helps removing air bubbles from the coating.

Note! Add the remaining mixture to the next batch of the product, do not scrape it out of the container onto the floor.



Temafloor PU-UV

HEALTH AND SAFETY

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

For industrial and professional use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

Temafloor PU-UV

EN 1504-2:2004

The European harmonized product standard EN 1504-2:2004 defines the requirements for surface protection systems for concrete.

This product is tested and CE-labelled in accordance with the tables 1d, 1f and 1g in the appendix ZA.

CE	
0809	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA	
13	
0809-CPD-0773	
TIK-0473-5001	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO ₂	$s_D > 50 \text{ m}$
Impact resistance	Class I: $\geq 4 \text{ Nm}$
Capillary absorption and permeability to water	$w < 0,1 \text{ kg/m}^2 \cdot h^{0,5}$
Abrasion resistance	$< 3000 \text{ mg}$
Reaction to fire	B _{f1} -s1
Behaviour after artificial weathering	no visual defects
Adhesion strength by pull off test	$\geq 2,0 \text{ N/mm}^2$
Release of dangerous substances	NPD
Permeability to water vapour	Class II, $5 \text{ m} < s_D < 50 \text{ m}$
Resistance to severe chemical attack	Class II